

Quality Description, A – Planed

| | |
|---------------|---|
| Quality: | Lunawood® Thermo-D |
| Raw Material: | Pine (Pinus Sylvestris), Spruce (Picea Abies) |
| Surface: | Planed |
| Installation: | Decking, External Cladding, Window Trims |
| Moisture: | 6 % ± 2 % after production |
| Tolerances: | |
| Width | ± 0,50 mm |
| Thickness | ± 0,50 mm |
| Length | - 10 mm, + 30 mm |

General Quality Evaluation

- The influence of a single defect is evaluated by looking at the overall quality of the product.
- Board is rejected if its overall look remarkably differs from the general quality requirements.
- Several maximum defects in one product are allowed if the overall look remains acceptable.
- In general 8 cm from the ends of the boards are not sorted. However end matched product are an exception.





Small knothole (not throughout) on a board is allowed.



Single crack of a knot is allowed.



Pitch pockets are allowed.



Small missing knot on the edge is allowed.



Defects which are invisible after installation are allowed.



Small scars may appear.



Small black knot on the edge is allowed.



Small shakes on the surface are allowed.