

## Quality Description, A – Planed

Quality:	Lunawood® Thermo-D
Raw Material:	Pine (Pinus Sylvestris), Spruce (Picea Abies)
Surface:	Planed
Installation:	Decking
Moisture:	6 % ± 2 % after production
Tolerances:	
Width	± 0,50 mm
Thickness	± 0,50 mm
Length	- 10 mm, + 30 mm

### General Quality Evaluation

- The influence of a single defect is evaluated by looking at the overall quality of the product.
- Board is rejected if its overall look remarkably differs from the general quality requirements.
- Several maximum defects in one product are allowed if the overall look remains acceptable.
- In general 8 cm from the ends of the boards are not sorted. However end matched product are an exception.







**Small knothole (not throughout) on a board is allowed.**



**Single crack of a knot is allowed.**



**Pitch pockets are allowed**



**Small missing knot is allowed.**



**Small split of a knot on the edge is allowed.**



**Small scars may appear.**



**In general 8 cm from the ends of the boards are not sorted.**



**Small shakes on the surface are allowed.**